

## PU Sealer / PU Anticolor



### List of proofed substances / chemical resistance

Tested floor: homogeneous sheet vinyl; curing time of sealer: 7 days

Exposure time of tested substances: approx. 30 minutes

### Explanation:

- Obvious damage or discolouration
- o Slight discolouration / shades
- + No discolouration or damage

	PU Sealer	PU Anticolor
	PU Sealer Antislip	
<b>Inorganic acids</b>		
Perchloric acid	+	+
Phosphoric acid (85 %)	—	—
Nitric acid (concentrated, 65 %)	—	—
Nitric acid (diluted, 12,5 %)	—	—
Hydrochloric acid (25 %)	—	+
Hydrochloric acid (diluted, 7,3 %)	—	+
Sulfuric acid (concentrated, 95 - 97 %)	—	—
Sulfuric acid (diluted, 9,8 %)	o	o
Hydrogenperoxide solution (39 %)	+	o / +
Hydrogenperoxide solution (3 %)	+	+
<b>Inorganic bases</b>		
Ammonia solution (concentrated, 25-30 %)	+	+
Ammonia solution (diluted, 10 %)	+	+
Barium hydroxide solution (4,73 %)	+	+
Sodium carbonate solution (10,6 %)	+	+
Sodium hydroxide solution (concentrated, 40 %)	o	+
Sodium hydroxide solution (diluted, 8,5 %)	o	+
Sodium hydrogen phosphate solution (9 %)	+	+
<b>Organic acids and bases</b>		
Formic acid	o / —	+
Acetic acid (30 %)	+	+
Acetic acid (diluted, 12 %)	+	+
Tartaric acid solution (15 %)	o	+

## PU Sealer / PU Anticolor



Diethylamine	0	+
Chloramine-T solution	+	+
Naphtylamine solution (0,3 %) in acetic acid (30 %)	—	—
<b>Organic solvents</b>		
Pentane / Hexane / Heptane	+	+
Petroleum ether / Gasoline	+	+
Cyclohexane	+	+
Toluene / Xylene	+	+
Acetone / Ethyl methyl ketone, Butanone	+	+
Ether	+	+
Methanol / Ethanol (90 % / 96 %)	+	+
1-Propanol / Isopropanol	+	+
Acetic acid anhydride	+	+
Ethyl acetate / Butyl acetate	+	+
Acetonitrile	+	+
<b>pH indicator solutions</b>		
Thymol blue	—	+
Methyl orange	—	+
Methyl red	—	—
Phenolphthalein	+	0
Phenol red	—	+
<b>Miscellaneous</b>		
Ammonium chloride solution (10,7 %)	+	+
Ammonium chloride, buffer solution (pH = 10,0)	+	+
Ammonium ferric (III) sulfate solution (10 %)	+	+
Ammonium molybdate solution (10,0 %)	+	+
Ammonium oxalate solution (4 %)	+	+
Ammonium thiocyanate solution (7,6 %)	—	0
Barium chloride solution (6,1%)	+	+
Iron(III) chloride solution (10,5 %)	—	+
Potassium hexacyanoferrate(II) solution (5,3 %)	+	+
Potassium hexacyanoferrate(III) solution (5 %)	+	+
Potassium hexahydroxoantimonate(V) solution	+	+
Potassium permanganate	0	+

## PU Sealer / PU Anticolor



Silver nitrate solution (1,7 % )	—	—
Starch solution	+	+
<b>Pharmaceutical / Medical reagents</b>		
Collodion	0	+
Iodine solution	—	+
Camomile extrakt	—	+
Thyme extrakt	—	+
Sulfanilic acid (1 %) in acetic acid (30 %)	+	+
Glyoxal-bis(2-hydroxyanil) (0,2 %) in ethanol (96 %)	—	—

### Dr. Schutz - Die Marke für Bodenreinigung und -pflege.

Entwicklung · Produktion · Logistik  
 CC-Dr. Schutz GmbH  
 Steinbrinksweg 30 · D-31840 Hessisch Oldendorf  
 Telefon: +49-(0)5152-9779-16  
 Fax: +49-(0)5152-9779-26  
 technik@dr-schutz.com · www.dr-schutz.com

The above advice for technical application is given to the best of our knowledge and according to the latest state of technology. Therefore, if our products are used carefully heeding the advice given on their application, as well as following our suggested procedures with the materials intended for use with these products, no damage shall occur. However, our products are used outside and beyond our possible control, and are therefore subject to your own responsibility, which does not release you from the obligation to check for yourself whether our supplied products are suitable for your intended purpose and procedure. Therefore our notes and advice are not legally binding and cannot be used against us as grounds for liability - which includes the rights and protection of any third party. The relevant recommendations, guidelines and standard norms are to be observed, as well as the recognized technical rules. On publication, this product information replaces and supersedes the validity of any previous versions.